

{W:\20692\0205266us0\00836447.DOC {XX}}

Claim 5 (currently amended): The biodegradable wrap film as recited in ~~any of Claims 1 to 4~~Claim 1, wherein the difference ($\Delta H_m - \Delta H_c$) is 10 J/g or more between ΔH_m , the heat of melting required to melt the crystals completely when heating the film according to JIS K-7121 at a heating rate of 10°C/minute using a differential scanning calorimeter, and ΔH_c , the heat of crystallization produced concomitantly with crystallization during the heating.

Claim 6 (currently amended): The biodegradable wrap film as recited in ~~any of Claims 1 to 5~~Claim 1, wherein the formed film is heated at a temperature between the glass transition temperature when heating according to JIS K-7121 at a heating rate of 10°C/minute using a differential scanning calorimeter, and the peak temperature of the heat of crystallization produced concomitantly with crystallization during the heating, and cured for 6 hours or longer.

Claim 7 (new): A biodegradable wrap film, comprising, as a main component, a lactic acid resin composition comprising:


a poly(DL-lactic acid) in which the proportion of L-isomer and D-isomer is 88:12 to 85:15 or 12:88 to 15:85, and

a plasticizer, wherein the lactic acid resin composition comprises a lactic acid resin and a plasticizer in a proportion of 60:40 to 99:1 by mass,

wherein the value of storage modulus at 20°C is in the range of 1 GPa to 4 GPa, as measured at a frequency of 10 Hz and a distortion of 0.1% by the dynamic viscoelasticity testing method from Method A of JIS K-7198, and the value of loss tangent ($\tan \delta$) at 20°C is 0.5 or less,

the value of storage modulus at 40°C is in the range of 100 MPa to 3 GPa, the value of storage modulus at 60°C is in the range of 100 MPa to 800 MPa, and the value of storage modulus at 100°C is in the range of 30 MPa to 500 MPa as measured at a frequency of 10 Hz and a distortion of 0.1% by the dynamic viscoelasticity testing method from Method A of JIS K-7198, and the peak value of loss tangent ($\tan \delta$) is in the range of 0.1 to 0.8.

Claim 8 (new): The biodegradable wrap film as recited in Claim 7, wherein the difference ($\Delta H_m - \Delta H_c$) is 10 J/g or more between ΔH_m , the heat of melting required to melt the crystals

{W:\20692\0205266us0\00836447.DOC  }

